

Cox Sales Company
2035 Cook Drive
Salem, Virginia 24153 USA
TEL: (540)345-2636 FAX: (540)342-8684

CoxTack 566

PRODUCT DATA SHEET

CoxTack 566 is a two part Acrylic emulsion based pressure sensitive adhesive designed for Removable Labels. Its outstanding traits are as follows:

- Excellent removability from a variety of substrates. Particularly effective for use on corrugated and outstanding release from glass.
- Suitable for film or paper labels.
- Superior anchorage, minimal adhesive transfer.

TYPICAL PHYSICAL CHARACTERISTICS

TYPICAL PERFORMANCE

Peel:400g/25mm(stainless)**Shear:**60 min SF (40°C x 1kg/sq/inch)**Preparation of sample:**
Face:Paper **Coating:**20mm **Dry:**120°C x 1 minute **Aging:**23°C, 65% RH x 7 days
Hardener:A-3 at 1 %

TYPICAL HANDLING AND APPLICATION

Shelf Life:	6 Months	Clean Up:	Water (wet), Solvent (dry)
Storage:	A Building at Ambient Temperatures	Protect From:	Freezing Temperatures
Diluent:	Water	Freeze Thaw Stable:	No

CoxTack 566 Application Information

A) Full anchorage will be attained after aging coated/laminated stock for 7 days at 23°C.

Because we cannot anticipate nor control the many different conditions under which this information and our products may be used, we do not guarantee the applicability or the accuracy of this information or the suitability of our products in any given situation. Users of our product should make their own tests to determine the suitability of each such product for their particular purposes. The products discussed are sold without warranty, either express or implied, and the buyer assumes all responsibility for loss or damage arising from the handling or use of our products, whether done in accordance with directions or not. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent.

Cox Sales Company
2035 Cook Drive
Salem, Virginia 24153 USA
TEL: (540)345-2636 FAX: (540)342-8684

- B) When CoxTack 566 is used with a 1% addition of A-3, the pot life will be approximately 8 hours.
- C) The A-3 must be thoroughly mixed for optimum results.

Because we cannot anticipate nor control the many different conditions under which this information and our products may be used, we do not guarantee the applicability or the accuracy of this information or the suitability of our products in any given situation. Users of our product should make their own tests to determine the suitability of each such product for their particular purposes. The products discussed are sold without warranty, either express or implied, and the buyer assumes all responsibility for loss or damage arising from the handling or use of our products, whether done in accordance with directions or not. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent.